

OPALJET MILLENIUM 3

100% Synthetic oil "FUEL ECONOMY" for PSA

120048/10.18

Rev. 4

DESCRIPTION & APPLICATIONS

OPALJET MILLENIUM 3 is a premium oil for reduced fuel consumption (up to 8% on some models PSA), and longer drain intervals.

OPALJET MILLENIUM 3 guarantees full protection of the exhaustgas aftertreatment systems (soot filters in particular).

Caution: This oil is not suitable for the lubrication of engines where no A5 / B5 standards are required. When in doubt, please contact us.

OPALJET MILLENIUM 3 is compatible with all motor oils, synthetic or mineral, but the high performance and exceptional features can only be guaranteed if the oil is used pure.

ADVANTAGES

- OPALJET MILLENIUM 3 protects particulate filters against pollution.
- OPALJET MILLENIUM 3 is little volatile and unshearable because its 100% synthetic nature.
- OPALJET MILLENIUM 3 ensures the cleanliness of all engine parts, prevents the formation of "sludge" at high and low temperatures, and allows extended drain intervals. (According to the recommendations of the manufacturer).
- OPALJET MILLENIUM 3 is officially PSA factory homologated: PSA B71 2290 (each model except PSA 1.8 l / 2.0 l / 2.2 l petrol)

PERFORMANCES

Satisfies to the following specifications:

ACEA C2-16

API CF/SN

FIAT 9,55535-S1/G1

IVECO 18-1811 SC1

PSA B 71 2290

OPALJET MILLENIUM 3

ENVIRONMENT, HEALTH & SAFETY

Please consult also the Safety Data Sheet about how to manipulate and to stock the product as well as to learn about the first aid measurements in case of accident.

Elimination after use must be made in conformity with the local rules in force about used oils disposal. When needed, Safety Data Sheet can be obtained upon request.

Conservation of the product: 3 year(s) in closed container and sheltered.

PROPERTIES

CHARACTERISTICS	UNITS	METHODS	TYPICAL DATA
SAE grade	-	-	5W30
Specific gravity at 15°C	kg/m ³	NFT 60101	852
Kinematic viscosity at 40°C	mm ² /s (cSt)	NFT 60100	57,1
Kinematic viscosity at 100°C	mm ² /s (cSt)	NFT 60100	10,1
Viscosity index	-	NFT 60136	167
Dynamic viscosity at -30°C	mPa.s	ASTM D 5293	5460
Flash point	°C	NFT 60118	232
Pour point	°C	NFT 60105	-39
Noack evaporation loss	% wheight	CEC-L-40-T-87	10,1
Sulphated ash content	% wheight	NF T 60143	0,8

The average values are given for information only.